



VISCOSITY

Product Data Sheet

Revised: 2022/02/21 (version 4)

VISCOSITY TUTELA Calcium Sulfonate Grease

Engineered with Fluid Technology Solutions™, our expertly designed formulation provides high performance and an extended protection for your off-road equipment.

Your number one priority is making sure your off-road equipment is always on the move. It's the engine of your business! When your equipment operates in the most extreme conditions- it requires high performance in adverse environments. Damage components lead to downtime which slow down your operations.



Description and Applications

VISCOSITY TUTELA Calcium Sulfonate Grease is a robust grease engineered to provide protection to key components or small parts on the equipment **to keep your work in fluid motion.**



Rust & Corrosion Protection



Temperature Range



Wear Protection

VISCOSITY TUTELA Calcium Sulfonate Grease is an extreme-pressure grease for use in agricultural, construction, automotive and industrial equipment. It's designed for use in conventional and disc brake wheel bearings, universal joints, spline shafts, water pumps and general chassis lubrication. It provides excellent low- and high-temperature performance

Benefits

- **Excellent wear protection** for the key components in your equipment preventing failure and downtime.
- **Outstanding protection against yellow metal corrosion** ensuring long life of sensitive components.
- **Outstanding oxidation stability** preventing the grease from breaking down allowing proper lubrication in tough applications

Approvals, Specifications and Recommendations

- NLGI Grade 2
- MAT 3555-D
- MAT 3550-D

Note: Always consult your owner's manual to check recommended viscosity grade and specifications for your specific vehicle

Typical Physical Data

Parameters	Method	Unit	Typical Value
NLGI Grade		2	
Soap Type		Calcium Sulfonate Complex	
Color		Tan	
Worked Penetration, 60 Strokes	ASTM D217	280	
Dropping Point	ASTM D2265	>300	°C
Four Ball EP Weld	ASTM D2596	500	Kg
Base Oil Viscosity, 40C	ASTM D445	220	cSt
Water Washout, 175F	ASTM D1264	3	%

Note: When dispensing from a grease gun, it's highly recommended that the grease be released at 0°C or above.

All technical data is provided for reference only. These characteristics are typical of current production. Whilst future production will conform to VISCOSITY's specification, variations in these characteristics may occur.

Health, Safety and Environment

This product is unlikely to present any significant health and safety hazards when used in the recommended application. Avoid contact with skin. Wash immediately with soap and water after skin contact. Do not discharge into drains, soil or water. For further detail regarding storage, safe handling, and disposal of product, please refer to product SDS or contact us at: www.viscosityoil.com

Important Note

VISCOSITY Documents and the information contained herein is believed to be accurate as of the date of printing. VISCOSITY Documents information provided is based on standard tests under laboratory conditions and is given only as a guide. Users are advised to ensure that they refer to the latest version of these VISCOSITY Documents. It is the responsibility of the users to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations imposed by the respective local authorities.

Safety Data Sheets are available for all our products and should only be consulted for appropriate information regarding storage, safe handling and disposal of the product. No responsibility shall be taken by either VISCOSITY or its subsidiaries and related holding corporation for any loss or injury or any direct, indirect, special, exemplary, consequential damages or any damages whatsoever, whether in action of contract, negligence or other tortious action, in connection or resulting from abnormal use of the materials and/or information, from any failure to adhere to recommendations, or from hazards inherent in the nature of the materials and/or information. All products, services and information supplied are under our standard conditions of sale. Please consult with any of our local representative in the event you require any further information.